

# Maintenance Guidelines

Talc

283767

**maharam**

## Maintenance Code

D-Dry clean only.



## Regular Maintenance

Professional dry cleaning is recommended.

Use a 2-5 minute cycle with low moisture level. Extract gently. Tumble dry for 10-20 minutes. Temperature should not to exceed 140°F. Open-weave textiles are best restored by air drying.

Hand Iron

Iron at low heat setting (275°F) with damp press cloth, or steam iron with dry press cloth.

Grid Head Press

Press for short intervals and with minimum steam. Do not lock head.

Flat Bed Press

Press dampened drapery using cloth covering.

Avoid prolonged contact with heat.

## Notes

The information above is a guide to help in the maintenance of Maharam textiles. Maharam can neither guarantee, nor take responsibility for specific results.

Under no circumstances shall Maharam be liable for any incidental, consequential, or other damage resulting from negligence, misuse, mishandling, or exposure of any chemicals used in connection with maintenance. Information relating to chemicals/cleaning solvents, environmental use, and human exposure should be reviewed with appropriate suppliers. All label instructions on their use and precautions should be followed.